



AMENDMENTS TO THE CLAIMS

1. (Currently Amended) A multi-branched polymer having repeating units represented by a formula (I):




wherein R_1 to R_3 each independently represents hydrogen or a hydrocarbon group, R_1 may be bonded to R_3 to form a ring; X represents a connecting group having a valence of 3 or higher; Y may be the same or different and each represents a functional group ~~which may have an active halogen atom~~ with a structure where a halogen atom becomes an active halogen atom when the halogen atom is bound to a constituting carbon atom; and a is an integer of 2 or larger.

2. (Original) The multi-branched polymer according to claim 1, wherein the repeating units represented by the formula (I) are repeating units represented by a formula (II):




wherein R_1 to R_3 are as defined above; Z represents a single bond or a connecting group having a valence of 2 or higher; A represents an aromatic hydrocarbon group or an aromatic heterocyclic group; R_4 may be the same or different and each represents a functional group which may have an active halogen atom; b is an integer of 2 or larger; R_5 represents a halogen atom or an organic group and d is 0 or an integer of 1 or larger and R_5 may be the same or different when d is 2 or larger.

3. (Original) The multi-branched polymer according to claim 2, wherein in the formula (II), Z is a single bond; A is an aromatic hydrocarbon ring; and R_4 is a functional group represented by a formula (III):




wherein R_6 and R_7 each independently represents hydrogen, a halogen atom, an alkyl group which may have a substituent, or a linkage with other repeating units with a proviso that R_6 and R_7 do not become linkages with other repeating units at the same time.

4. (Original) The multi-branched polymer according to claim 1, wherein the repeating units represented by the formula (I) are repeating units represented by a formula (IV):




wherein R_1 to R_3 , Y , and a are as defined above; and V represents a connecting group having a valence of 3 or higher.

5. (Previously Presented) The multi-branched polymer according to claim 4, wherein V is a polyoxyalkylene group in the formula (IV).
6. (Original) The multi-branched polymer according to claim 4 or 5, wherein in the formula (IV), Y is a functional group represented by a formula (V):




wherein R_{61} and R_{71} each independently represents hydrogen, a halogen atom, an alkyl group which may have a substituent, or a linkage with other repeating units with a proviso that R_{61} and R_{71} do not become linkages with other repeating units at the same time.

7. (Currently Amended) A multi-branched polymer obtained with a living radical polymerization method using a metal catalyst by polymerizing compounds represented by a formula (VI):




wherein R₈ to R₁₀ each independently represents hydrogen or a hydrocarbon group, and R₈ may be bonded to R₁₀ to form a ring; X₁ represents a connecting group having a valence of 3 or higher; Y₁ may be the same or different and each represents a functional group ~~which may have an active halogen atom~~ with a structure where a halogen atom becomes an active halogen atom when the halogen atom is bound to a constituting carbon atom; a₁ is an integer of 2 or larger; and R₁₁ represents a chlorine atom, a bromine atom, or an iodine atom.

8. (Original) The multi-branched polymer according to claim 7, wherein the compounds represented by the formula (VI) are compounds represented by a formula (VII):




wherein R_8 to R_{10} are as defined above; Z_1 represents a single bond or a connecting group having a valence of 2 or higher; A1 represents an aromatic hydrocarbon group or an aromatic heterocyclic group; R_{24} may be the same or different and each represents a functional group which may have an active halogen atom; $b1$ is an integer of 2 or larger; R_{25} represents a halogen atom or an organic group and $d1$ is 0 or an integer of 1 or larger and R_{25} may be the same or different when $d1$ is 2 or larger; R_{26} represents a chlorine atom, a bromine atom, or an iodine atom.

9. (Original) The multi-branched polymer according to claim 8, wherein in the formula (VII), Z_1 is a single bond, A1 is an aromatic hydrocarbon group, and R_{24} is a functional group represented by a formula (VIII):



wherein R_{60} and R_{70} each independently represents hydrogen, a halogen atom, or a C1 to C6 alkyl group which may have a substituent with a proviso that R_{60} and R_{70} are not halogen atoms other than fluorine atoms at the same time.


10. (Original) The multi-branched polymer according to claim 7, wherein the compounds represented by the formula (VI) are compounds represented by a formula (IX):



wherein R_8 to R_{10} are as defined above respectively; V_{11} represents a connecting group having a valence of 3 or higher; Y_1 may be the same or different and each represents a functional group which may have an active halogen atom; $a1$ is an integer of 2 or larger; and R_{11} represents a chlorine atom, a bromine atom, or an iodine atom.

11. (Previously Presented) The multi-branched polymer according to claim 10, wherein V_{11} is a polyoxyalkylene group in the formula (IX).

12. (Original) The multi-branched polymer according to claim 10 or 11, wherein in the formula (IX), Y_1 is a functional group represented by a formula (X):



wherein R_{610} and R_{710} each independently represents hydrogen, a halogen atom, an alkyl group which may have a substituent, or a linkage with other repeating units with a proviso that R_{610} and R_{710} do not become linkages with other repeating units at the same time.

13. (Previously Presented) The multi-branched polymer according to claim 1 or 7, wherein a ratio (M_w/M_n) of weight average molecular weight (M_w) to number average molecular weight (M_n) of the polymer is in a range between 1.01 and 9.99.

14. (Previously Presented) The multi-branched polymer according to claim 1 or 7, wherein the number average molecular weight (M_n) of the polymer is in a range between 200 and 20,000,000.

15. (Previously Presented) The multi-branched polymer according to claim 1 or 7, wherein the multi-branched polymer is a hyperbranched polymer.

16 – 19 (Cancelled)

20. (Currently amended) A star polymer having the multi-branched polymer according to claim 1 or 7 ~~or the hyperbranched polymer according to claim 16 or 17 as a core thereof.~~